

FONDO TURAPORI TRASPARENTE ALLA NITRO PER INTERNO

Fondo trasparente turapori a rapida essiccazione, dotato di ottimo potere riempitivo, alta resa, buona carteggiabilità, elasticità e resistenza alla sovraverniciatura.

Per l'applicazione si consigliano 2/3 riprese dopo aver carteggiato il supporto con abrasivi grana 100.

Il prodotto è sovraverniciabile dopo circa 4 ore, previa carteggiatura, con le finiture Nitrolux HRS 200 clear o Nitropack HRS 350 clear.

VISCOSITY:	DIN 4 20 C°	60 sec. +/- 2 sec.
VISCOSITY MIX A + B:	DIN 4 20 C°	
SPECIFIC GRAVITY:	20 C°	0.98 gr/lt +/- 0.01
SOLID CONTENT:	120 C° 1 hour	26% +/- 1%
SOLID CONTENT A + B:	120 C° 1 hour	
DILUTION:	30% D110 → 20" DIN 4	
POT LIFE:	20 C°	
DRYING TO DUST:	20 C°	10 min +/- 10 min.
DRYING TO TOUCH:	20 C°	15 min +/- 10 min.
DRYING TO SANDING:	20 C°	24 hours +/- 2 h.
FINAL DRYING:	20 C°	24 hours +/- 2 h.

GLOSS %				
PACKAGING	5 LT.	10 LT.	25 LT.	
APPLICATION:	SPRAY – AIRLESS – AIRMIX - SPRAY GUN			
HARDENING:				
NUMBER OF LAYERS:	1 - 2			
QUANTITY:	150 gr/mq			